VINYL COMPOSITION TILE (VCT)

Standard Excelon® Imperial® Texture

Exclusive Fast Start® Factory Finish

Through-Color/Pattern Wear Layer

Product Information

Construction - Vinyl Composition Tile

International Specifications - ASTM F1066 - Class 2 Through Pattern, ISO 10595, Type II Overall/Wear Layer Thickness - 1/8 in. (3.2 mm), 3/32 in. (2.4 mm)

Factory Finish - Fast Start®

Installation - Adhesives: S-515, S-525, S-1000

Maintenance Options - Polish

+1/8" and 3/32" sizes are stocked for these colors: 51830, 51836, 51839, 51858, 51899 All other colors are stocked in 1/8" size; 3/32" is available on a special order basis, minimum order quantity of 45,000 sq ft² (4,181 m²).

Packaging

Size	Tile per Carton/Coverage	Shipping Weight per Carton
12 in. x 12 in. (305 mm x 305 mm)	45 - 45 ft ² (4.18 m ²)	1/8 in 63 lbs./carton (28.6 kg) 3/32 in 48 lbs./carton (21.7 kg)

Testing

ASTM F1066				
Performance	Test Method	Requirement	Performance vs. Requirement	
Thickness	ASTM F386	Nominal ± 0.005 in.	Meets	
Size	ASTM F2055	± 0.016 in. per linear foot	Meets	
Squareness	ASTM F2055	0.010 in. max	Meets	
ndentation – One Minute	ASTM F1914	≥ 0.006 in. to ≤ 0.015 in.	Meets	
Indentation @ 115°F	ASTM F1914	< 0.032 in.	Meets	
Impact	ASTM F1265	No cracks beyond limit	Meets	
Deflection	ASTM F1304	1.0 in. minimum	Meets	
Dimensional Stability	ASTM F2199	≤ 0.024 in. per linear foot	Meets	
Chemical Resistance	ASTM F925	No more than slight change in surface dulling, attack or staining	Meets	
Resistance to Heat	ASTM F1514	$\Delta E < 8.0$	Meets	
Additional Testing				
Static Load Resistance	ASTM F970*	< 0.005 in.	2000 psi	
Fire Test Data – Flame Spread	ASTM E648	0.45 W/cm ² or more Class 1	Meets	
Fire Test Data – Smoke Evolution	ASTM E662	450 or less	Meets	
Fire Test Data – Canada	CAN\ULC S102.2	Use dependent	Flame Spread - 0 Smoke Developed - 30	
ADA Standards for Accessible Design	Chapter 3 Section 302.1	Floor surfaces shall be stable, firm and slip-resistant	Meets	
tatic Coefficient of Friction** ASTM D 2047/UL 410 ≥ 0.5		≥ 0.5	Meets	

Maritime Usage

IMO Resolution A653 (16)

Surface Flammability IMO MSC 61(67) Annex 1 Part 5 and Annex 2 Smoke and Toxicity IMO MSC 61(67) Annex 1 Part 2 and Annex 2

Passes Passes Compliant

Safety Of Life at Sea (SOLAS)

Approved

ArmstrongFlooring[®]

VINYL COMPOSITION TILE (VCT)

Standard Excelon® Imperial® Texture

Sustainability

WELL v1 Fea	ture	Imperial Texture	Contribution	
Air	Feature 04 - VOC Reduction	✓	Tested and third party certified by FloorScore® as complying with CDPH v1.2	
	Feature 11 - Fundamental Material Safety	✓	Product is free of asbestos and added lead (Part 1)	
	Feature 25 - Toxic Material Reduction	1	Free of flame retardants (Part 2)	
Mind	Feature 97 - Material Transparency	1	Readily available Health Product Declaration® (HPD) to 1000 ppm	
	Feature 88 (Part 2) Biophilia I - Qualitative	1	Products available that incorporate nature patterns	
	Feature 99 - Beauty and Design II		Patterns and colors to aid in wayfinding and spatial familiarity (Part 3)	
WELL v2 Fea	ature	Imperial Texture	Contribution	
Air	Feature X12 - Short Term Emission Control	✓	Adhesives associated with product are tested and third party certified by FloorScore as complying with CDPH v1.2	
	Feature X11 Long-Term Emission Control	✓	Flooring is tested and third party certified by FloorScore as complying with CDPH v1.2	
	Feature X01 Fundamental Material Precautions	✓	Product is free of asbestos	
Materials	Feature X10 Volatile Organic Compound	1	Free of flame retardants (Part 2)	
	Feature X14 Material Transparency	<i>✓</i>	Readily available Health Product Declaration® (HPD) to 1000 ppm	
Mind	Feature MO2 Access to Nature	✓ ✓	Products available that incorporate nature patterns	
Community	Feature C13 (Part 2) Accessibility and Universal Design		Patterns and colors to aid in wayfinding and spatial familiarity	
LEED [™] v4.1		Imperial Texture		
BPDO - EPD		Product Specific certif	Product Specific certified by ASTM International	
BPDO - Materia	I Ingredient			
BPDO - Sourcir	ığ	'	ntent – 25% Total (5% Post-Consumer and 20% Pre-Consumer) oducer Responsibility – On&On™ Recycling Program	
Location of Ma	nufacturer	USA		
Low Emitting F	looring	Tested and third party	certified by FloorScore as complying with CDPH v1.2	
Low Emitting Adhesives		Tested and compliant to CDPH v1.2; Methylene Chloride and Perchloroethylene not intentionally added; FloorScore Certified		
SCAQMD #1168 Compliant. S		S-515 – 0 g/L		
Adhesives mee	et <50 g/L requirement.	S-525 – 16 g/L		
		S-1000 – 0.1 g/L		

Carbon Footprint	Imperial Text
Global Warming Potential, including Biogenic Carbon	0.33 Kg CO ² eq.
Raw Materials (A1) through Production (A3)	(3.52 Kg CO ² eq.

ture

1. / square foot q. / square meter)

Limited Warranty

5-year Commercial Warranty when installed in strict accordance with the detailed instructions.

Visit ArmstrongFlooring.com

for complete Product, Technical, Adhesives, Installation & Maintenance recommendations.

F9717-522

20203 AHF, LLC. Armstrong Flooring and the Armstrong Flooring logo are under license from AWI Licensing LLC. | FloorScore® is a registered trademark of the Resilient Floor Covering Institute [LEED® is a registered trademarks of the United States Green Building Council The Health Product Declaration® logo is a registered trademark of HPD Collaborative. All other trademarks are the property of AHF, LLC.

*Testing at loads above 125 psi is outside the scope of the test method. Since testing is conducted on uninstalled flooring, results do not consider the performance of the adhesive, underlayment, or subfloor. These test results are not an indicator of the installed flooring system performance. **Using the James Machine as described in D2047 and as directed in UL 410 for floor covering materials (FCM) using a leather foot under dry conditions. The application of site-applied floor sealers, polishes and other types of finishes routinely used to maintain The application of site-applied floor sealers, polishes and other types of finishes routinely used to maintain resilient flooring materials will change the walking surface and consequently the SCOF value.

