



OUR FAMILY OF BRANDS.



Vinyl Based Tile (VBT™) Flooring

Testing Results

TEST METHOD CONDUCTED: ASTM F925 (Regular) Standard Test Method for Resistance to Chemicals of Resilient Flooring

STAINING AGENT	5 MINUTE RATINGS		
	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid	No Change	No Change	No Change
70% Isopropyl Alcohol	No Change	No Change	No Change
Mineral Oil	No Change	No Change	No Change
5% Sodium Hydroxide	No Change	No Change	No Change
5% Hydrochloric Acid	No Change	No Change	No Change
5% Ammonia	No Change	No Change	No Change
Bleach	No Change	No Change	No Change
5% Phenol	No Change	No Change	No Change
Gasoline	No Change	No Change	No Change
Sulfuric Acid	No Change	No Change	No Change
Kerosene	No Change	No Change	No Change
Olive Oil	No Change	No Change	No Change

STAINING AGENT	24 HOUR RATINGS		
	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid	No Change	No Change	No Change
70% Isopropyl Alcohol	No Change	No Change	No Change
Mineral Oil	No Change	No Change	No Change
5% Sodium Hydroxide	No Change	No Change	No Change
5% Hydrochloric Acid	No Change	No Change	No Change
5% Ammonia	No Change	No Change	No Change
Bleach	No Change	No Change	No Change
5% Phenol	No Change	No Change	No Change
Gasoline	No Change	No Change	No Change
Sulfuric Acid	No Change	No Change	No Change
Kerosene	No Change	No Change	No Change
Olive Oil	No Change	No Change	No Change