



OUR FAMILY OF BRANDS.



# LVT Flooring with HartGuard™ Finish

## Testing Results

TEST METHOD CONDUCTED: ASTM F925 Standard Test Method for Resistance to Chemicals of Resilient Flooring

| STAINING AGENT                     | 5 MINUTE RATINGS |                |               |
|------------------------------------|------------------|----------------|---------------|
|                                    | SURFACE DULLING  | SURFACE ATTACK | COLOR CHANGE  |
| Blood                              | No Change        | No Change      | No Change     |
| Betadine                           | No Change        | No Change      | No Change     |
| Iodine                             | No Change        | No Change      | No Change     |
| Methylene Blue                     | No Change        | No Change      | No Change     |
| A456 II Germicide                  | No Change        | No Change      | No Change     |
| Lemon Eze                          | No Change        | No Change      | No Change     |
| QC 52 Glass Cleaner                | No Change        | No Change      | No Change     |
| QC 53 General Purpose Cleaner      | No Change        | No Change      | No Change     |
| QC 31 Neutral Cleaner              | No Change        | No Change      | No Change     |
| Ecoshine Stainless Steel Polish    | No Change        | No Change      | No Change     |
| Lime A Way                         | No Change        | No Change      | No Change     |
| Bleach 10%                         | No Change        | No Change      | No Change     |
| Disinfectants: Phenolic/Quaternary | No Change        | No Change      | Slight Change |
| Permanent Marker                   | No Change        | No Change      | Severe Change |
| Acetone                            | No Change        | No Change      | No Change     |
| Hair Dye                           | No Change        | No Change      | Severe Change |

| STAINING AGENT                     | 24 HOUR RATINGS |                |               |
|------------------------------------|-----------------|----------------|---------------|
|                                    | SURFACE DULLING | SURFACE ATTACK | COLOR CHANGE  |
| Blood                              | No Change       | No Change      | No Change     |
| Betadine                           | No Change       | No Change      | No Change     |
| Iodine                             | No Change       | No Change      | No Change     |
| Methylene Blue                     | No Change       | No Change      | No Change     |
| A456 II Germicide                  | No Change       | No Change      | No Change     |
| Lemon Eze                          | No Change       | No Change      | No Change     |
| QC 52 Glass Cleaner                | No Change       | No Change      | No Change     |
| QC 53 General Purpose Cleaner      | No Change       | No Change      | No Change     |
| QC 31 Neutral Cleaner              | No Change       | No Change      | No Change     |
| Ecoshine Stainless Steel Polish    | No Change       | No Change      | No Change     |
| Lime A Way                         | No Change       | No Change      | No Change     |
| Bleach 10%                         | No Change       | No Change      | No Change     |
| Disinfectants: Phenolic/Quaternary | No Change       | No Change      | Slight Change |
| Permanent Marker                   | No Change       | No Change      | Severe Change |
| Acetone                            | No Change       | No Change      | No Change     |
| Hair Dye                           | No Change       | No Change      | Severe Change |



OUR FAMILY OF BRANDS.



# LVT Flooring with HartGuard™ Finish

## Testing Results

TEST METHOD CONDUCTED: ASTM F925 Standard Test Method for Resistance to Chemicals of Resilient Flooring

| STAINING AGENT          | 5 MINUTE RATINGS |                |                 |
|-------------------------|------------------|----------------|-----------------|
|                         | SURFACE DULLING  | SURFACE ATTACK | COLOR CHANGE    |
| Mineral Spirits         | No Change        | No Change      | No Change       |
| Red Kool Aid            | No Change        | No Change      | No Change       |
| Red Wine                | No Change        | No Change      | No Change       |
| Shoe Polish Paste Brown | No Change        | No Change      | Moderate Change |
| Aniline Blue            | No Change        | No Change      | No Change       |
| Ball Point Pen          | No Change        | No Change      | No Change       |
| Bicarbonate             | No Change        | No Change      | No Change       |
| Cherry Soda             | No Change        | No Change      | No Change       |
| Ethyl Alcohol           | No Change        | No Change      | No Change       |
| Hematoxylin             | No Change        | No Change      | No Change       |
| Potassium Permanganate  | No Change        | No Change      | Severe Change   |
| Tar                     | No Change        | No Change      | Moderate Change |
| Yellow Mustard          | No Change        | No Change      | No Change       |
| Purell                  | No Change        | No Change      | No Change       |

| STAINING AGENT          | 24 HOUR RATINGS |                |                 |
|-------------------------|-----------------|----------------|-----------------|
|                         | SURFACE DULLING | SURFACE ATTACK | COLOR CHANGE    |
| Mineral Spirits         | No Change       | No Change      | No Change       |
| Red Kool Aid            | No Change       | No Change      | No Change       |
| Red Wine                | No Change       | No Change      | No Change       |
| Shoe Polish Paste Brown | No Change       | No Change      | Moderate Change |
| Aniline Blue            | No Change       | No Change      | No Change       |
| Ball Point Pen          | No Change       | No Change      | No Change       |
| Bicarbonate             | No Change       | No Change      | No Change       |
| Cherry Soda             | No Change       | No Change      | No Change       |
| Ethyl Alcohol           | No Change       | No Change      | No Change       |
| Hematoxylin             | No Change       | No Change      | No Change       |
| Potassium Permanganate  | No Change       | No Change      | Severe Change   |
| Tar                     | No Change       | No Change      | Moderate Change |
| Yellow Mustard          | No Change       | No Change      | No Change       |
| Purell                  | No Change       | No Change      | No Change       |