

Resistance to Staining Reagents

MedinPure PVC-Free Homogeneous Sheet

We extensively test all our products to determine how our different flooring products will perform in use — and, how the flooring will react to staining reagents. Owners and specifiers know the types of substances that may potentially stain surfaces in their building. This chart is designed to provide owners and specifiers with accurate information about a wide variety of cleaners, disinfectants, foods, beverages, oils, organic solvent, and other substances that may be found in buildings and affect the performance of the floor.

Organic Solvents	MedinPure PVC-Free Sheet
Acetone	0
Chloroform	0
Ethyl Acetate	0
Ethyl (Denatured) Alcohol	0
Ethyl Ether	0
Ethylene Glycol (Antifreeze)	0
Formaldehyde - 10%	0
Gasoline	0
Isopropyl Alcohol	0
Kerosene	0
Methyl ethyl ketone (M.E.K.)	0
Mineral Spirits	0
Toluene	0
Trichloroethylene	0
Turpentine	0
Xylene	0
Alkali (Bases)	MedinPure PVC-Free Sheet
Ammonium Hydroxide - 30%	0
Potassium Hydroxide - 15%	2
Sodium Hydroxide - 50%	0
Acids	MedinPure PVC-Free Sheet
Acetic Acid - 28%	0
Acetic Acid - Glacial	0
Hydrochloric - 38%	0
Lactic Acid - 10%	0
Nitric Acid - 15%	0
Phosphoric Acid - 85%	0
Sulfuric Acid - 40%	0
Sulfuric Acid - 10%	0
Salt Solutions	MedinPure PVC-Free Sheet
Calcium Chloride - Sat'd	0
Copper Sulfate - 10%	0
Ferric Chloride - 10%	0
Silver Nitrate - 1%	0

Resistance to Staining Reagents

Medical Stains & Reagents	MedinPure PVC-Free Sheet
Aniline Blue - 2.5%	0
Auramine Rhodamine	3
Basic Fuchsin	2
Betadine ® Skin Cleanser	1
Betadine ® Solution - 10%	1
Bromcresol Green	2
Carbol Fuchsin	3
Eosin - 1%	0
Gentian Violet - 2%	3
Glutaraldehyde	0
Iodine Tincture	3
Iodine Gram Stain	3
Iodoform - 1%	0
Lugol's Solution	3
Merthiolate Tincture	1
Methylene Blue	1
Picric Acid - 1%	1
Potassium Permanganate - 0.5%	3
Tincture of Benzoin	3, R
Urea Solution	0
Wright's Blood Stain	3
Disinfectants and Cleaners	MedinPure PVC-Free Sheet
Bleach - 5.25% sodium hypochlorite	1
Comet Bathroom Cleaner	0
Hydrogen Peroxide	0
Lysol ® Liquid Disinfectant	0
Food Service	MedinPure PVC-Free Sheet
Catsup	0
Coffee - Hot Black	0
Cola Drink	0
French Dressing	0
Mustard	2
Red Food Color	2
Red Wine	0
Soy Sauce	0
Spaghetti Sauce	0
Tea - Hot Black	0
Tomato Paste	0

Resistance to Staining Reagents

Office		MedinPure PVC-Free Sheet
Ball Pen Ink		3
Carbon Paper Smudge		1
Fountain Pen Ink		0
Lead Pencil		1
Permanent Black Marker		3
Red Crayon		0
Red Tempura Paint		0
Oils		MedinPure PVC-Free Sheet
Beef Tallow - Hot		0
Canola Oil		0
Cottonseed Oil		0
Brake Fluid		0
Dextron Transmission Fluid		0
Mineral Oil		0
Olive Oil		0
SAE #10 Oil		0
30 wt. Non-Detergent Oil		0
Used Motor Oil		0
Miscellaneous		MedinPure PVC-Free Sheet
Asphalt Driveway Sealer		0
Blue Chalk		0
Black Rit Dye		0
Eye Shadow		1
Hair Color		3
Lipstick		1
Perfume		0
Red Candle Wax		0
Red Nail Polish		1, R
Shoe Polish - Liquid Brown		0
Shoe Polish - Paste Brown		1

Resistance to Staining Reagents

Samples were tested as manufactured (no additional surface treatments). All samples were exposed to reagents for 4 hours (uncovered), then cleaned with a neutral commercial cleaner and cotton cloth. A key for interpreting results is found below. It is important to note that in some cases, residual stain, residues, and surface dulling may be further reduced or eliminated with different or more aggressive cleaning procedures and/or cleaning agents other than the common method used for this multi-product comparison. For further details on appropriate cleaning methods and care for specific products, please consult the care and maintenance guidelines for the specific product at ArmstrongFlooring.com or contact Armstrong Flooring at 866 243 2726.

- | | |
|------------|--------------------------|
| 0 No Stain | BI Bleaching |
| 1 Slight | D Dulling |
| 2 Moderate | G Gloss up |
| 3 Severe | S Softening |
| | R Reagent left a residue |