

Product Information

Construction - Homogeneous

International Specifications - ASTM F1913

Overall Thickness - 0.080 in. (2.0 mm)


Wear Layer Thickness - 0.080 in. (2.0 mm)

Factory Finish - Commercial Polyurethane Coating

Installation - Full-Spread Adhesives: S-995

Seams: Heat Weld or S-761 Seam Adhesive

Maintenance Options - No Polish - No Buff, Polish Optional



Packaging

Roll Length	Roll Width	Shipping Weight per Roll
Up to 52.5 ft. (16 m)	6 ft. (1.83 m)	Approx. 225 lbs./sq. yd. (110 kg/m ²)

Testing

ASTM F1913			
Performance	Test Method	Requirement	Performance vs. Requirement
Thickness	ASTM F386	≥ 0.075 in.	Meets
Residual Indentation	ASTM F1914	≤ 0.007 in.	Meets
Chemical Resistance	ASTM F925	No more than slight change in surface dulling, attack or staining	Meets
Resistance to Heat	ASTM F1514	ΔE ≤ 8	Meets
Resistance to Light	ASTM F1515	ΔE ≤ 8	Meets
Static Load Resistance @ 250	ASTM F970	≤ 0.005 in.	Meets
Flexibility	ASTM F1317	No cracks/breaks (1.5 in. / 38 mm Mandrel)	Meets
Additional Testing			
Fire Test Data – Flame Spread	ASTM E648	0.45 W/cm ² or more Class 1	Meets
Fire Test Data – Smoke Evolution	ASTM E662	450 or less	Meets
Static Coefficient of Friction**	ASTM D2047/UL 410	≥ 0.5	Meets

Limited Warranty

10-year Commercial Warranty when installed in strict accordance with the detailed instructions.

Add 10 years of overall warranty coverage by using Strong System™ subfloor preparation products.

AF-1050-423

Armstrong and the Armstrong logo are under license from AWI Licensing LLC. | All other trademarks are owned by AHF Products LLC. | © 2023 AHF Products LLC. FloorScore® is a registered trademark of the Resilient Floor Covering Institute. | LEED® is a registered trademark of the United States Green Building Council. The Health Product Declaration® logo is a registered trademark of HPD Collaborative.

*Testing at loads above 250 psi is outside the scope of the test method. Since testing is conducted on uninstalled flooring, results do not consider the performance of the adhesive, underlayment, or subfloor. These test results are not an indicator of the installed flooring system performance.** Using the James Machine as described in D2047 and as directed in UL 410 for floor covering materials (FCM) using a leather foot under dry conditions. The application of site-applied floor sealers, polishes and other types of finishes routinely used to maintain resilient flooring materials will change the walking surface and consequently the SCOF value.

